

HRPB 750

*Product Specifications

Test Item	Unit	Test Method	Specification
Color(AHPA)	–	ASTM D1209	Max 50
Viscosity(100°C)	cSt	ASTM D445	80 ~ 105
Molecular Weight	–	GPC	700 ~ 800
Dispersity(Mw/Mn)	–	GPC	Max 1.47
Flash Point(COC)	°C	ASTM D92	Min 160
Flash Point(PM)	°C	ASTM D93B	Min 125
α-Vinylidene	Wt-%	13C NMR	Min 80
Acid Value	mgKOH/g	ASTM D974	Max 0.01
Water	Wt-ppm	ASTM D6304	Max 40

Properties of DAELIM PolyButene

- Water-White Color (transparent viscous liquid)
- Non Odor & Non-Toxic & High Purity
- Tacky
- Hydrophobic & Inertness
- Excellent Stability of Oxidant and UV Light
- Superior Shear Stability
- Excellent Electrical Insulating Properties
- Great Water Repellency (very low moisture transmission rates)
- Outstanding Lubricity & Permanently Non-Drying
- Clean Decomposition & No Residue
- Low Pour Points & Superior Viscosity Index(VI)
- Non-Staining Characteristics (non-corrosive)

**Typical Value of HRPB 750

Typical Properties	Unit	Test Method	Typical Value
Molecular Weight (Mn)	–	GPC(Gel Permeation Chromatography)	750
Kinetic Viscosity(40°C)	cSt	ASTM D445	2,200
Kinetic Viscosity(100°C)	cSt	ASTM D445	90
Flash Point(COC)	°C	ASTM D92(Cleveland Open Cup)	200
Flash Point(PM)	°C	ASTM D93B(Pensky-Martens)	150
α-Vinylidene	Wt-%	13C NMR	83
Color(AHPA)	–	ASTM D1209	15
Pour Point	°C	ASTM D97	-10
Loss on Heating	Wt-%	KS C2101	0.25
Water	Wt-ppm	ASTM D6304	20
Acid Value	mgKOH/g	ASTM D974	0.01
Total Sulfur	Wt-ppm	ASTM D2785	1
Dielectric Constant(80°C)	–	ASTM D924	2.18
Dielectric Breakdown Voltage(2.5mm)	kV	ASTM D149	40

Important Notice to User

The result on this technical data are reliable under the limited conditions and methods mentioned. It should be needed the user to get suitability for commercial use.

Application

- Additives
 - Lubricant Oil Additive(Dispersant), Fuel Oil Additive(Detergent)
 - Emulsifier(Explosive Emulsifier)
 - LOA/FOA & Emulsifier intermediate(polyisobutenyl succinic anhydride, PIBSA) prepared from HRPB
- Lubricants
- Caulks & Sealants

Cautions and Recommendations

Preliminary statement For safe handling information on this product, consult the Material Safety Data Sheets (MSDS)

*Handling

- Wear protective gloves/ protective clothing/ eye protection/ face protection
- Maintain below flash point, protect to leak of liquid or vapor.
- Keep away from open flames, shut off the production of source of ignition (electricity/electricity sparks/heat/material of high-temperature)
- Ground/bond all container and receiving equipment, use equipment of prevention of explosion.
- Do not breathe vapor or mist when using this material. Avoid prolonged or repeated contact with skin. Avoid contact with eyes.
- Empty containers may contain harmful, flammable/combustible or explosive residue or vapors.
- Wash thoroughly after handling.

Storage

- Keep container tightly closed in a cool, well-ventilated place.
- Keep container tightly closed before use.
- Avoid contact with incompatible materials.
- Keep away from heat, sparks, open flames, source of ignition.
- Suitable storage materials : mild steel/ carbon steel

Hazards Identification

- GHS Classification : Not Classifiable
- GHS label elements
 - Hazard symbols : Not Classifiable
 - Signal word : Not Classifiable
 - Hazard statement : Not Classifiable
 - Precautionary statements : Not Classifiable
- Other hazards which do not result in classification
 - May causes irritation if contact with eyes, skin, mucous membranes.
 - If contact with non-refrigerated product, may causes burns.
 - NFPA Classification(0~4 steps) : Health=1, Flammability=1, Reactivity=0
 - HMIS Classification(0~4 steps) : Health=1, Flammability=1, Reactivity=0

Health and Safety

Health and Safety Guidance on Health and Safety are available on the appropriate Material Safety Data Sheets (MSDS) that can be obtained from DAELIM Industrial Co., Ltd. representative.

Understand the Material Safety Data Sheets (MSDS) for additional information on personal protective equipment and for safety, health, environmental & toxicology information, first aid measures, ecological & regulatory information.

If additional information is required, please contact the below.

Contact Information

Y.H. Hwang
General Manager
DAELIM Corporation Co., Ltd.
Tel.: +82-2-3708-3468
Fax: +82-2-754-1142
E-mail) yhhwang@daelimcorp.co.kr

Visit Us at Our Website

For the most direct access to local sales and technical support visit:
www.daelimchem.co.kr

The information is to our best present knowledge correct and complete and is given in good faith but without warranty. This information is supplied for informational purposes only, and without any guarantee or warranty, expressed or implied, regarding its accuracy, correctness, or completeness. This information only concerns the above-mentioned product and does not need to be valid if used with other(s) or in any process. It remains the user's own responsibility to make sure that the information is appropriate and sufficiently complete for their particular use of this product. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for the customer's specific use. The applicable Material Safety Data Sheet should be reviewed by customer before handling the DAELIM Industrial Co., Ltd. product. This information is believed to be accurate as of the date of publication.

Copyright ©2012 DAELIM Industrial Co., Ltd. All Right Reserved.